


DECLARATION OF PERFORMANCE OF THE „ARPANEL” SANDWICH PANELS

NO. DWU/CH PIR/1/2026/EN

1	Name and address of manufacturer	Adamietz S.A. 47 – 100 Strzelce Opolskie ul. Braci Prankel 1 Poland
2	Unique identification code of the product-type	ARPANEL CH 120 PIR, ARPANEL CH 140 PIR, ARPANEL CH 160 PIR, ARPANEL CH 200 PIR SANDWICH PANELS with polyisocyanurate foam core.
3	Intended use, in accordance with the applicable harmonized technical specification	Metal faced insulating panel for use in buildings as external walls, partitions and ceilings.
4	System of assessment and verification of constancy of performance:	System 3
5	Harmonized standard	PN-EN 14509:2013 - 12
6	Notified body	- INSTYTUT TECHNIKI BUDOWLANEJ Warsaw – No. 1488 - IMA Materialforschung und Anwendungstechnik GmbH Dresden – No. 2456 - Fires s.r.o. Batizovce – No. 1396
7	Declared performance	Annex 1.

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



PROKURENT
Marcin Sobisiak

Strzelce Opolskie, 24-03-2026

ADAMIETZ S.A.
ARPANEL – PŁYTY WARSTWOWE
ul. Braci Prankel 1 47-100 Strzelce Opolskie
tel. +48 77 463 00 65 fax +48 77 463 92 00
NIP 756-18-36-633 REGON 532242263



Annex 1 to the Declaration of performance NO. DWU/CH PIR/01/2026/EN

Panel thickness [mm]	120	140	160	200		
Dimensional tolerances	± 2 %					
Mass [kg/m ²]	12,6	13,4	14,2	15,7		
Density of core material (PIR foam) [kg/m ³]	40±3					
External/Internal Facing - Steel grade	S280GD+Z; S250GD+Z; S220GD+Z					
Coating type	SP25, Food Safe (PVC), PRISMA, HDX, PVDF, PUR/PA					
Thickness of facing material [mm]	External: 0,5 - 0,7		Internal: 0,4 - 0,7			
Facing profile	External: G, L, M8, M14, M30		Internal: G, L, M20			
Cross panel tensile strength f_{ct} [kPa]	100	98	95	90		
Compressive strength (core) f_{cc} [kPa]	100	100	100	100		
Shear strength (core) f_{cv} [kPa]	120	113	105	90		
Shear modulus (core) G_c [MPa]	3,1	2,9	2,7	2,3		
Creep coefficient	t= 2.000 h	3,0				
	t= 100.000 h	5,0				
Wrinkling stress [MPa]	in span	external face	M8/M14:195	M8/M14:195	M8/M14:195	M8/M14:195
			M30: 184	M30: 176,5	M30: 169	M30: 154
			L:134 G:63	L:129 G:61	L:124 G:60	L:113 G:57
		external face >80°C	M8/M14:158	M8/M14:158	M8/M14:158	M8/M14:158
			M30: 149	M30: 143	M30: 137	M30: 125
			L:109 G:51	L:105 G:50	L:101 G:49	L:92 G:46
	internal face	L:134 G:63	L:129 G:62	L:124 G:60	L:113 G:57	
		M20:184	M20:177	M20:169	M20:154	
		At central support	external face	M8/M14:137	M8/M14:132	M8/M14:127
	M30: 129			M30: 119,8	M30: 110,5	M30: 89,5
	L:90 G:44			L:85 G:42	L:79 G:39	L:68 G:34
	external face >80°C		M8/M14:111	M8/M14:107	M8/M14:103	M8/M14:95
			M30: 104	M30: 96,8	M30: 89,5	M30: 75
			L:73 G:36	L:69 G:34	L:64 G:32	L:55 G:28
	internal face	L:114 G:54	L:108 G: 52	L:102 G:50	L:90 G:46	
		M20:133	M20:123	M20:113	M20:92	
Correction factors for the thickness of the facing		t=0,6 mm for M8/14: 0,85 for M20/M30: 0,83 for L: 0,84 t=0,7 mm for M8/14:0,76 for M20/M30:0,74 for L: 0,75				
Thermal conductivity λ_D [W/m*K]	0,022					
Thermal transmittance $U_{d,s}$ [W/m ² *K]	0,18	0,16	0,14	0,11		
Reaction to fire	B-s1,d0					
Fire resistance*	Vertical	E 30 / EI 30			E 60 / EI 45 / EW 60	
	Horizontal	E 30 / EI 30 / EW 30			E 45 / EI 45 / EW 45	
	Ceiling	EI 30 (a←b)				
Water permeability [class]	A					
Air permeability	Positive pressure	C = 0,2630; n = 0,5313				
	Negative pressure	C = 0,0227; n = 0,4764				
Airborne sound insulation R_w (C, Ctr) [dB]	24 (-2;-4)					
Sound absorption α_w	0,15					
Additional performance not included in the list of relevant clauses in accordance with PN-EN 14509:						
Parameter	Value					
Fire-spread	non-fire spreading					
λ_{design} [W/m*K] (0°C)	0,021					
$U_{d,s}$ [W/m ² *K] (0°C)	0,17	0,15	0,13	0,10		

